

Fiche technique NEOWRAP QUANTUM

Ref astic : 30860

Palette 46 bobines

Physical / Mechanical Characteristics	Value	Rules	Tolerances
POLYMER	LLDPE		
THICKNESS	12 my		+/- 1 my
WIDTH	500 mm		+/- 2 %
COLOR	TRANSPARENT		
TENSILE STRENGTH	MD: 32 N/mm ²	ASTM D 882	+/- 10 %
	TD: 24 N/mm ²		
YIELD STRENGTH	MD: 7,0 N/mm ²	ASTM D 882	+/- 10 %
	TD: 6,8 N/mm ²		
ELONGATION AT BREAK	MD: 600 %	ASTM D 882	+/- 10 %
	TD: 815 %		
ELONGATION IN USE	300 %	INTERNAL METHOD	+/- 10 %
DART TEST	80 g	INTERNAL METHOD	+/- 10 %